



## DEPARTMENT OF COMMERCE

### International Trade Administration

[C-570-048, C-580-888]

Certain Carbon and Alloy Steel Cut-to-Length Plate from the People's Republic of China and the Republic of Korea: Continuation of Countervailing Duty Orders

AGENCY: Enforcement and Compliance, International Trade Administration, Department of Commerce.

SUMMARY: As a result of the determinations by the U.S. Department of Commerce (Commerce) and the U.S. International Trade Commission (ITC) that revocation of the countervailing duty (CVD) orders on certain carbon and alloy steel cut-to-length plate (CTL plate) from the People's Republic of China (China) and the Republic of Korea (Korea) would likely lead to a continuation or recurrence of net countervailable subsidies and material injury to an industry in the United States, Commerce is publishing a notice of continuation of these CVD orders.

DATES: Applicable [Insert date of publication in the *Federal Register*].

FOR FURTHER INFORMATION CONTACT: Faris Montgomery, AD/CVD Operations, Office VIII, Enforcement and Compliance, International Trade Administration, U.S. Department of Commerce, 1401 Constitution Avenue, NW, Washington, DC 20230; telephone: (202) 482-1537.

### SUPPLEMENTARY INFORMATION:

#### Background

On March 20 and May 25, 2017, respectively, Commerce published the CVD orders on CTL plate from China and Korea.<sup>1</sup> On December 1, 2021, Commerce initiated,<sup>2</sup> and the ITC

---

<sup>1</sup> See *Certain Carbon and Alloy Steel Cut-to-Length Plate from the People's Republic of China: Countervailing Duty Order*, 82 FR 14346 (March 20, 2017); see also *Certain Carbon and Alloy Steel Cut-to-Length Plate from the Republic of Korea: Countervailing Duty Order*, 82 FR 24103 (May 25, 2017) (collectively, *Orders*).

<sup>2</sup> See *Initiation of Five-Year (Sunset) Reviews*, 86 FR 68220 (December 1, 2021).

instituted,<sup>3</sup> sunset reviews of the *Orders*, pursuant to section 751(c)(2) of the Tariff Act of 1930, as amended (the Act). Commerce conducted expedited (120-day) sunset reviews of the *Orders*, pursuant to section 751(c)(3)(B) of the Act and 19 CFR 351.218(e)(1)(ii)(C)(2).

As a result of its reviews, Commerce determined, pursuant to sections 751(c)(1) and 752(b) of the Act, that revocation of the *Orders* would likely lead to continuation or recurrence of countervailable subsidies. Therefore, Commerce notified the ITC of the magnitude of the net countervailable subsidy rates likely to prevail should these *Orders* be revoked.<sup>4</sup>

On February 3, 2023, the ITC published its determinations, pursuant to section 751(c) of the Act, that revocation of the *Orders* would likely lead to a continuation or recurrence of material injury to an industry in the United States within a reasonably foreseeable time.<sup>5</sup>

#### Scope of the *Orders*

The product covered by the *Orders* is CTL plate. For complete descriptions of the scope of the *Orders*, see the appendix to this notice.

#### Continuation of the *Orders*

As a result of the determinations by Commerce and the ITC that revocation of the *Orders* would likely lead to a continuation or recurrence of countervailable subsidies, as well as material injury to an industry in the United States, pursuant to section 751(d)(2) of the Act and 19 CFR 351.218(a), Commerce hereby orders the continuation of the *Orders*.

U.S. Customs and Border Protection will continue to collect CVD cash deposits at the rates in effect at the time of entry for all imports of subject merchandise from China and Korea.

---

<sup>3</sup> See *Carbon and Alloy Steel Cut-to-Length Plate from Austria, Belgium, Brazil, China, France, Germany, Italy, Japan, Korea, South Africa, Taiwan, and Turkey: Institution of Five-Year Reviews*, 86 FR 68269 (December 1, 2021).

<sup>4</sup> See *Certain Carbon and Alloy Steel Cut-to-Length Plate from the People's Republic of China: Final Results of the Expedited First Sunset Review of the Countervailing Duty Order*, 87 FR 17068 (March 25, 2022), and accompanying Issues and Decision Memorandum (IDM); see also *Certain Carbon and Alloy Steel Cut-to-Length Plate from the Republic of Korea: Final Results of the Expedited First Sunset Review of the Countervailing Duty Order*, 87 FR 19070 (April 1, 2022), and accompanying IDM.

<sup>5</sup> See *Carbon and Alloy Steel Cut-to-Length Plate from Austria, Belgium, Brazil, China, France, Germany, Italy, Japan, South Africa, South Korea, Taiwan, and Turkey*, 88 FR 7462 (February 3, 2023); see also *Carbon and Alloy Steel Cut-to-Length Plate from Austria, Belgium, Brazil, China, France, Germany, Italy, Japan, South Africa, South Korea, Taiwan, and Turkey*, Investigation Nos. 701-TA-560-561 and 731-TA-1317-1328 (Review), USITC Pub. 5399 (January 2023).

The effective date of the continuation of the *Orders* will be the date of publication in the *Federal Register* of this notice of continuation. Pursuant to section 751(c)(2) of the Act and 19 CFR 351.218(c)(2), Commerce intends to initiate the next five-year (sunset) review of the *Orders* not later than 30 days prior to the fifth anniversary of the effective date of continuation.

#### Administrative Protective Order

This notice also serves as the only reminder to parties subject to an administrative protective order (APO) of their responsibility concerning the return, destruction, or conversion to judicial protective order of proprietary information disclosed under APO in accordance with 19 CFR 351.305(a)(3), which continues to govern business proprietary information in this segment of the proceedings. Timely written notification of the return or destruction of APO materials, or conversion to judicial protective order, is hereby requested. Failure to comply is a violation of the APO which may be subject to sanctions.

#### Notification to Interested Parties

We are issuing and publishing this notice in accordance with sections 751(c) and (d)(2) and 777(i)(1) of the Act and 19 CFR 351.218(f)(4).

Dated: February 9, 2023.

/s/ Lisa W. Wang

---

Lisa W. Wang,  
Assistant Secretary  
for Enforcement and Compliance.

## Appendix

### Scope of the *Orders*

#### *CTL Plate from China*

The products covered by this *Order* are certain carbon and alloy steel hot-rolled or forged flat plate products not in coils, whether or not painted, varnished, or coated with plastics or other non-metallic substances (cut-to-length plate). Subject merchandise includes plate that is produced by being cut-to-length from coils or from other discrete length plate and plate that is rolled or forged into a discrete length. The products covered include: (1) universal mill plates (*i.e.*, flat-rolled products rolled on four faces or in a closed box pass, of a width exceeding 150 mm but not exceeding 1250 mm, and of a thickness of not less than 4 mm, which are not in coils and without patterns in relief); and (2) hot-rolled or forged flat steel products of a thickness of 4.75 mm or more and of a width which exceeds 150 mm and measures at least twice the thickness, and which are not in coils, whether or not with patterns in relief. The covered products described above may be rectangular, square, circular or other shapes and include products of either rectangular or non-rectangular cross-section where such non-rectangular cross-section is achieved subsequent to the rolling process, *i.e.*, products which have been “worked after rolling” (*e.g.*, products which have been beveled or rounded at the edges).

For purposes of the width and thickness requirements referenced above, the following rules apply:

- (1) except where otherwise stated where the nominal and actual thickness or width measurements vary, a product from a given subject country is within the scope if application of either the nominal or actual measurement would place it within the scope based on the definitions set forth above; and
- (2) where the width and thickness vary for a specific product (*e.g.*, the thickness of certain products with non-rectangular cross-section, the width of certain products with non-rectangular shape, *etc.*), the measurement at its greatest width or thickness applies.

Steel products included in the scope of this *Order* are products in which: (1) iron predominates, by weight, over each of the other contained elements; and (2) the carbon content is 2 percent or less by weight.

Subject merchandise includes cut-to-length plate that has been further processed in the subject country or a third country, including but not limited to pickling, oiling, levelling, annealing, tempering, temper rolling, skin passing, painting, varnishing, trimming, cutting, punching, beveling, and/or slitting, or any other processing that would not otherwise remove the merchandise from the scope of the *Order* if performed in the country of manufacture of the cut-to-length plate.

All products that meet the written physical description, are within the scope of this *Order* unless specifically excluded or covered by the scope of an existing order. The following products are outside of, and/or specifically excluded from, the scope of this *Order*:

- (1) products clad, plated, or coated with metal, whether or not painted, varnished or coated with plastic or other non-metallic substances;

(2) military grade armor plate certified to one of the following specifications or to a specification that references and incorporates one of the following specifications:

- MIL-A-12560,
- MIL-DTL-12560H,
- MIL-DTL-12560J,
- MIL-DTL-12560K,
- MIL-DTL-32332,
- MIL-A-46100D,
- MIL-DTL-46100-E,
- MIL-46177C,
- MIL-S-16216K Grade HY80,
- MIL-S-16216K Grade HY100,
- MIL-S-24645A HSLA-80;
- MIL-S-24645A HSLA-100,
- T9074-BD-GIB-010/0300 Grade HY80,
- T9074-BD-GIB-010/0300 Grade HY100,
- T9074-BD-GIB-010/0300 Grade HSLA80,
- T9074-BD-GIB-010/0300 Grade HSLA100, and
- T9074-BD-GIB-010/0300 Mod. Grade HSLA115,

except that any cut-to-length plate certified to one of the above specifications, or to a military grade armor specification that references and incorporates one of the above specifications, will not be excluded from the scope if it is also dual – or multiple-certified to any other non-armor specification that otherwise would fall within the scope of this *Order*;

(3) stainless steel plate, containing 10.5 percent or more of chromium by weight and not more than 1.2 percent of carbon by weight;

(4) CTL plate meeting the requirements of ASTM A-829, Grade E 4340 that are over 305 mm in actual thickness;

(5) Alloy forged and rolled CTL plate greater than or equal to 152.4 mm in actual thickness meeting each of the following requirements:

(a) Electric furnace melted, ladle refined & vacuum degassed and having a chemical composition (expressed in weight percentages):

- Carbon 0.23-0.28,
- Silicon 0.05-0.20,
- Manganese 1.20-1.60,
- Nickel not greater than 1.0,
- Sulfur not greater than 0.007,
- Phosphorus not greater than 0.020,
- Chromium 1.0-2.5,
- Molybdenum 0.35-0.80,
- Boron 0.002-0.004,
- Oxygen not greater than 20 ppm,
- Hydrogen not greater than 2 ppm, and
- Nitrogen not greater than 60 ppm;

(b) With a Brinell hardness measured in all parts of the product including mid thickness falling within one of the following ranges:

- (i) 270-300 HBW,
- (ii) 290-320 HBW, or
- (iii) 320-350HBW;

(c) Having cleanliness in accordance with ASTM E45 method A (Thin and Heavy): A not exceeding 1.5, B not exceeding 1.0, C not exceeding 0.5, D not exceeding 1.5; and

(d) Conforming to ASTM A578-S9 ultrasonic testing requirements with acceptance criteria 2 mm flat bottom hole;

(6) Alloy forged and rolled steel CTL plate over 407 mm in actual thickness and meeting the following requirements:

(a) Made from Electric Arc Furnace melted, Ladle refined & vacuum degassed, alloy steel with the following chemical composition (expressed in weight percentages):

- Carbon 0.23-0.28,
- Silicon 0.05-0.15,
- Manganese 1.20-1.50,
- Nickel not greater than 0.4,
- Sulfur not greater than 0.010,
- Phosphorus not greater than 0.020,
- Chromium 1.20-1.50,
- Molybdenum 0.35-0.55,
- Boron 0.002-0.004,
- Oxygen not greater than 20 ppm,
- Hydrogen not greater than 2 ppm, and
- Nitrogen not greater than 60 ppm;

(b) Having cleanliness in accordance with ASTM E45 method A (Thin and Heavy): A not exceeding 1.5, B not exceeding 1.5, C not exceeding 1.0, D not exceeding 1.5;

(c) Having the following mechanical properties:

(i) With a Brinell hardness not more than 237 HBW measured in all parts of the product including mid thickness; and having a Yield Strength of 75ksi min and UTS 95ksi or more, Elongation of 18% or more and Reduction of area 35% or more; having charpy V at -75 degrees F in the longitudinal direction equal or greater than 15 ft. lbs (single value) and equal or greater than 20 ft. lbs (average of 3 specimens) and conforming to the requirements of NACE MR01-75; or

(ii) With a Brinell hardness not less than 240 HBW measured in all parts of the product including mid thickness; and having a Yield Strength of 90 ksi min and UTS 110 ksi or more, Elongation of 15% or more and Reduction of area 30% or more; having charpy V at -40 degrees F in the longitudinal direction equal or greater than 21 ft. lbs (single value) and equal or greater than 31 ft. lbs (average of 3 specimens);

(d) Conforming to ASTM A578-S9 ultrasonic testing requirements with acceptance criteria 3.2 mm flat bottom hole; and

(e) Conforming to magnetic particle inspection in accordance with AMS 2301;

(7) Alloy forged and rolled steel CTL plate over 407 mm in actual thickness and meeting the following requirements:

(a) Made from Electric Arc Furnace melted, ladle refined & vacuum degassed, alloy steel with the following chemical composition (expressed in weight percentages):

- Carbon 0.25-0.30,
- Silicon not greater than 0.25,
- Manganese not greater than 0.50,
- Nickel 3.0-3.5,
- Sulfur not greater than 0.010,
- Phosphorus not greater than 0.020,
- Chromium 1.0-1.5,
- Molybdenum 0.6-0.9,
- Vanadium 0.08 to 0.12
- Boron 0.002-0.004,
- Oxygen not greater than 20 ppm,
- Hydrogen not greater than 2 ppm, and
- Nitrogen not greater than 60 ppm.

(b) Having cleanliness in accordance with ASTM E45 method A (Thin and Heavy): A not exceeding 1.0(t) and 0.5(h), B not exceeding 1.5(t) and 1.0(h), C not exceeding 1.0(t) and 0.5(h), and D not exceeding 1.5(t) and 1.0(h);

(c) Having the following mechanical properties: a Brinell hardness not less than 350 HBW measured in all parts of the product including mid thickness; and having a Yield Strength of 145ksi or more and UTS 160ksi or more, Elongation of 15% or more and Reduction of area 35% or more; having charpy V at -40 degrees F in the transverse direction equal or greater than 20 ft. lbs (single value) and equal or greater than 25 ft. lbs (average of 3 specimens);

(d) Conforming to ASTM A578-S9 ultrasonic testing requirements with acceptance criteria 3.2 mm flat bottom hole; and

(e) Conforming to magnetic particle inspection in accordance with AMS 2301.

The products subject to the *Order* are currently classified in the Harmonized Tariff Schedule of the United States (HTSUS) under item numbers: 7208.40.3030, 7208.40.3060, 7208.51.0030, 7208.51.0045, 7208.51.0060, 7208.52.0000, 7211.13.0000, 7211.14.0030, 7211.14.0045, 7225.40.1110, 7225.40.1180, 7225.40.3005, 7225.40.3050, 7226.20.0000, and 7226.91.5000.

The products subject to the *Order* may also enter under the following HTSUS item numbers: 7208.40.6060, 7208.53.0000, 7208.90.0000, 7210.70.3000, 7210.90.9000, 7211.19.1500, 7211.19.2000, 7211.19.4500, 7211.19.6000, 7211.19.7590, 7211.90.0000, 7212.40.1000, 7212.40.5000, 7212.50.0000, 7214.10.0000, 7214.30.0010, 7214.30.0080, 7214.91.0015, 7214.91.0016, 7214.91.0020, 7214.91.0060, 7214.91.0090, 7225.11.0000, 7225.19.0000, 7225.40.5110, 7225.40.5130, 7225.40.5160, 7225.40.7000, 7225.99.0010, 7225.99.0090,

7226.11.1000, 7226.11.9060, 7226.19.1000, 7226.19.9000, 7226.91.0500, 7226.91.1530, 7226.91.1560, 7226.91.2530, 7226.91.2560, 7226.91.7000, 7226.91.8000, and 7226.99.0180.

The HTSUS subheadings above are provided for convenience and customs purposes only. The written description of the scope of the *Order* is dispositive.

#### *CTL Plate from Korea*

The products covered by this *Order* are certain carbon and alloy steel hot-rolled or forged flat plate products not in coils, whether or not painted, varnished, or coated with plastics or other non-metallic substances (cut-to-length plate). Subject merchandise includes plate that is produced by being cut-to-length from coils or from other discrete length plate and plate that is rolled or forged into a discrete length. The products covered include: (1) universal mill plates (*i.e.*, flat-rolled products rolled on four faces or in a closed box pass, of a width exceeding 150 mm but not exceeding 1250 mm, and of a thickness of not less than 4 mm, which are not in coils and without patterns in relief); and (2) hot-rolled or forged flat steel products of a thickness of 4.75 mm or more and of a width which exceeds 150 mm and measures at least twice the thickness, and which are not in coils, whether or not with patterns in relief. The covered products described above may be rectangular, square, circular or other shapes and include products of either rectangular or non-rectangular cross-section where such non-rectangular cross-section is achieved subsequent to the rolling process, *i.e.*, products which have been “worked after rolling” (*e.g.*, products which have been beveled or rounded at the edges).

For purposes of the width and thickness requirements referenced above, the following rules apply:

- (8) except where otherwise stated where the nominal and actual thickness or width measurements vary, a product from a given subject country is within the scope if application of either the nominal or actual measurement would place it within the scope based on the definitions set forth above unless the product is already covered by an order existing on that specific country (*i.e.*, *Certain Hot-Rolled Steel Flat Products from Brazil and the Republic of Korea: Amended Final Affirmative Countervailing Duty Orders*, 81 FR 67960 (October 3, 2016)); and
- (9) where the width and thickness vary for a specific product (*e.g.*, the thickness of certain products with non-rectangular cross-section, the width of certain products with non-rectangular shape, *etc.*), the measurement at its greatest width or thickness applies.

Steel products included in the scope of this *Order* are products in which: (1) iron predominates, by weight, over each of the other contained elements; and (2) the carbon content is 2 percent or less by weight.

Subject merchandise includes cut-to-length plate that has been further processed in the subject country or a third country, including but not limited to pickling, oiling, levelling, annealing, tempering, temper rolling, skin passing, painting, varnishing, trimming, cutting, punching, beveling, and/or slitting, or any other processing that would not otherwise remove the merchandise from the scope of the *Order* if performed in the country of manufacture of the cut-to-length plate.

All products that meet the written physical description, are within the scope of this *Order* unless specifically excluded or covered by the scope of an existing order. The following products are outside of, and/or specifically excluded from, the scope of this *Order*:



- (1) products clad, plated, or coated with metal, whether or not painted, varnished or coated with plastic or other non-metallic substances;
- (2) military grade armor plate certified to one of the following specifications or to a specification that references and incorporates one of the following specifications:

- MIL-A-12560,
- MIL-DTL-12560H,
- MIL-DTL-12560J,
- MIL-DTL-12560K,
- MIL-DTL-32332,
- MIL-A-46100D,
- MIL-DTL-46100-E,
- MIL-46177C,
- MIL-S-16216K Grade HY80,
- MIL-S-16216K Grade HY100,
- MIL-S-24645A HSLA-80;
- MIL-S-24645A HSLA-100,
- T9074-BD-GIB-010/0300 Grade HY80,
- T9074-BD-GIB-010/0300 Grade HY100,
- T9074-BD-GIB-010/0300 Grade HSLA80,
- T9074-BD-GIB-010/0300 Grade HSLA100, and
- T9074-BD-GIB-010/0300 Mod. Grade HSLA115,

except that any cut-to-length plate certified to one of the above specifications, or to a military grade armor specification that references and incorporates one of the above specifications, will not be excluded from the scope if it is also dual – or multiple-certified to any other non-armor specification that otherwise would fall within the scope of this *Order*;

- (10) stainless steel plate, containing 10.5 percent or more of chromium by weight and not more than 1.2 percent of carbon by weight;
- (11) CTL plate meeting the requirements of ASTM A-829, Grade E 4340 that are over 305 mm in actual thickness;
- (12) Alloy forged and rolled CTL plate greater than or equal to 152.4 mm in actual thickness meeting each of the following requirements:
  - (a) Electric furnace melted, ladle refined & vacuum degassed and having a chemical composition (expressed in weight percentages):
    - Carbon 0.23-0.28,
    - Silicon 0.05-0.20,
    - Manganese 1.20-1.60,
    - Nickel not greater than 1.0,
    - Sulfur not greater than 0.007,
    - Phosphorus not greater than 0.020,
    - Chromium 1.0-2.5,
    - Molybdenum 0.35-0.80,
    - Boron 0.002-0.004,

- Oxygen not greater than 20 ppm,
- Hydrogen not greater than 2 ppm, and
- Nitrogen not greater than 60 ppm;

(b) With a Brinell hardness measured in all parts of the product including mid thickness falling within one of the following ranges:

- (i) 270-300 HBW,
- (ii) 290-320 HBW, or
- (iii) 320-350HBW;

(c) Having cleanliness in accordance with ASTM E45 method A (Thin and Heavy): A not exceeding 1.5, B not exceeding 1.0, C not exceeding 0.5, D not exceeding 1.5; and

(d) Conforming to ASTM A578-S9 ultrasonic testing requirements with acceptance criteria 2 mm flat bottom hole;

(13) Alloy forged and rolled steel CTL plate over 407 mm in actual thickness and meeting the following requirements:

(a) Made from Electric Arc Furnace melted, Ladle refined & vacuum degassed, alloy steel with the following chemical composition (expressed in weight percentages):

- Carbon 0.23-0.28,
- Silicon 0.05-0.15,
- Manganese 1.20-1.50,
- Nickel not greater than 0.4,
- Sulfur not greater than 0.010,
- Phosphorus not greater than 0.020,
- Chromium 1.20-1.50,
- Molybdenum 0.35-0.55,
- Boron 0.002-0.004,
- Oxygen not greater than 20 ppm,
- Hydrogen not greater than 2 ppm, and
- Nitrogen not greater than 60 ppm;

(b) Having cleanliness in accordance with ASTM E45 method A (Thin and Heavy): A not exceeding 1.5, B not exceeding 1.5, C not exceeding 1.0, D not exceeding 1.5;

(c) Having the following mechanical properties:

(i) With a Brinell hardness not more than 237 HBW measured in all parts of the product including mid thickness; and having a Yield Strength of 75ksi min and UTS 95ksi or more, Elongation of 18% or more and Reduction of area 35% or more; having charpy V at -75 degrees F in the longitudinal direction equal or greater than 15 ft. lbs (single value) and equal or greater than 20 ft. lbs (average of 3 specimens) and conforming to the requirements of NACE MR01-75; or

(ii) With a Brinell hardness not less than 240 HBW measured in all parts of the product including mid thickness; and having a Yield Strength of 90 ksi min and UTS 110 ksi or more, Elongation of 15% or more and Reduction of area 30% or more; having charpy V at -40 degrees F in the longitudinal direction equal or

greater than 21 ft. lbs (single value) and equal or greater than 31 ft. lbs (average of 3 specimens);

(d) Conforming to ASTM A578-S9 ultrasonic testing requirements with acceptance criteria 3.2 mm flat bottom hole; and

(e) Conforming to magnetic particle inspection in accordance with AMS 2301;

(14) Alloy forged and rolled steel CTL plate over 407 mm in actual thickness and meeting the following requirements:

(a) Made from Electric Arc Furnace melted, ladle refined & vacuum degassed, alloy steel with the following chemical composition (expressed in weight percentages):

- Carbon 0.25-0.30,
- Silicon not greater than 0.25,
- Manganese not greater than 0.50,
- Nickel 3.0-3.5,
- Sulfur not greater than 0.010,
- Phosphorus not greater than 0.020,
- Chromium 1.0-1.5,
- Molybdenum 0.6-0.9,
- Vanadium 0.08 to 0.12
- Boron 0.002-0.004,
- Oxygen not greater than 20 ppm,
- Hydrogen not greater than 2 ppm, and
- Nitrogen not greater than 60 ppm.

(b) Having cleanliness in accordance with ASTM E45 method A (Thin and Heavy): A not exceeding 1.0(t) and 0.5(h), B not exceeding 1.5(t) and 1.0(h), C not exceeding 1.0(t) and 0.5(h), and D not exceeding 1.5(t) and 1.0(h);

(c) Having the following mechanical properties: a Brinell hardness not less than 350 HBW measured in all parts of the product including mid thickness; and having a Yield Strength of 145ksi or more and UTS 160ksi or more, Elongation of 15% or more and Reduction of area 35% or more; having charpy V at -40 degrees F in the transverse direction equal or greater than 20 ft. lbs (single value) and equal or greater than 25 ft. lbs (average of 3 specimens);

(d) Conforming to ASTM A578-S9 ultrasonic testing requirements with acceptance criteria 3.2 mm flat bottom hole; and

(e) Conforming to magnetic particle inspection in accordance with AMS 2301.

At the time of the filing of the petition, there was an existing countervailing duty order on certain cut-to-length carbon-quality steel plate from Korea. *See Final Affirmative Countervailing Duty Determination: Certain Cut-to-Length Carbon-Quality Steel Plate from the Republic of Korea*, 64 FR 73176 (December 29, 1999), as amended, 65 FR 6587 (February 10, 2000) (*1999 Korea CVD Order*). The scope of the countervailing duty order with regard to cut-to-length plate from Korea covers only (1) subject cut-to-length plate not within the physical description of cut-to-length carbon quality steel plate in the *1999 Korea CVD Order* regardless of producer or exporter; and (2) cut-to-length plate produced and/or exported by those companies that were

excluded or revoked from the *1999 Korea CVD Order* as of April 8, 2016. The only revoked or excluded company is Pohang Iron and Steel Company, also known as POSCO.

The products subject to the *Order* are currently classified in the Harmonized Tariff Schedule of the United States (HTSUS) under item numbers: 7208.40.3030, 7208.40.3060, 7208.51.0030, 7208.51.0045, 7208.51.0060, 7208.52.0000, 7211.13.0000, 7211.14.0030, 7211.14.0045, 7225.40.1110, 7225.40.1180, 7225.40.3005, 7225.40.3050, 7226.20.0000, and 7226.91.5000.

The products subject to the *Order* may also enter under the following HTSUS item numbers: 7208.40.6060, 7208.53.0000, 7208.90.0000, 7210.70.3000, 7210.90.9000, 7211.19.1500, 7211.19.2000, 7211.19.4500, 7211.19.6000, 7211.19.7590, 7211.90.0000, 7212.40.1000, 7212.40.5000, 7212.50.0000, 7214.10.0000, 7214.30.0010, 7214.30.0080, 7214.91.0015, 7214.91.0060, 7214.91.0090, 7225.11.0000, 7225.19.0000, 7225.40.5110, 7225.40.5130, 7225.40.5160, 7225.40.7000, 7225.99.0010, 7225.99.0090, 7226.11.1000, 7226.11.9060, 7226.19.1000, 7226.19.9000, 7226.91.0500, 7226.91.1530, 7226.91.1560, 7226.91.2530, 7226.91.2560, 7226.91.7000, 7226.91.8000, and 7226.99.0180.

The HTSUS subheadings above are provided for convenience and customs purposes only. The written description of the scope of the *Order* is dispositive.

[FR Doc. 2023-03213 Filed: 2/14/2023 8:45 am; Publication Date: 2/15/2023]